



Wood Treated Right™

Specification Guide for Treated Wood End Uses

		Preservative Retention (Lbs. per cubic foot)	
		CA-C	μCA-C
AGRICULTURE, FARM USE	Round poles and posts as structural members	.31 ¹	.23
	Sawn poles and posts as structural members	.31 ¹	.23
	Posts, Fence		
	Round, half & quarter round	.15	.14
	Sawn four sides	.15	.14
	Lumber, in soil contact	.15	.14
	Lumber, not in soil contact	.060	.05
	Plywood, in soil contact	.15	.14
	Plywood, not in soil contact	.060	.05
	Grape stakes, sawn	.15	.14
BUILDING CONSTRUCTION MATERIAL	Floor plate	.060	.05
	Flooring, residential		
	Damp environment	.060	.05
	Dry environment	.060	.05
	Framing, interior	.060	.05
	Lumber		
	Interior, above ground	.060	.05
	Exterior, above ground	.060	.05
	Ground contact and fresh water use	.15	.14
	Permanent Wood Foundation		
	Lumber & Plywood	.31 ¹	.23
	Plywood		
	Sub-floor, damp above ground	.060	.05
	Exterior, above ground	.060	.05
	Ground contact and fresh water use	.15	.14
	Poles, building		
	Round	.31 ¹	.23
	Sawn	.31 ¹	.23
	Piling, foundation, land & freshwater		
	Round timber (Southern pine)	.41 ²	.33
DECKS	Above ground: Decking, joists, rails, steps	.060	.05
	Sapwood species: Decking, specialties	.060	.05
	Ground contact: Posts	.15	.14
FENCES	Pickets, slats, trim	.060	.05
	Posts, sawn	.15	.14
HIGHWAY MATERIAL	Lumber and timbers for bridges, structural members, decking, cribbing, & culverts	.31 ¹	.23
	Handrails and guardrails	.060	.05
	Structural lumber and timbers:		
	Posts: Round, half-round, quarter round	.15	.14
	Posts: Sawn	.15	.14
	Posts, guardrail		
	Round	.25	.23
	Sawn	.31	.23

¹ICC-ES accepts .25pcf

²ICC-ES accepts .35pcf

www.wolmanizedwood.com